



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Classic Pilaster Cap

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Classic Pilaster Caps provide distinctive good looks with high strength hardrock concrete. The Classic Pilaster Cap has a 2" bullnose edge with a ¼" top and bottom reveal. Classic Pilaster Caps are designed to be used for both commercial and residential applications.

Composition & Materials

Classic Pilaster Caps are hand-made, wet-cast from 4000 PSI hardrock concrete using Type III cement.

Sizes

Classic Pilaster Caps are available in standard sizes; 10"x18" (Flat only), 14"x14", 16"x16", 19"x19", 22"x22", 24"x24", and 28"x28" Flat Classic Pilaster Caps have a thickness of 2 ½"; peaked Classic Pilaster Caps thickness varies.

Finishes

Classic Pilaster Cap finishes include: standard smooth finish, light, medium, or heavy sandblast

Colors

Classic Pilaster Caps are available in 12 standard colors: Almond, Cafe Brown, Kona, Caramel, French Gray, Granada White, Iceberg Green, Pebble, Santa Fe Buff, Brick Red, Agave, Porcelain; custom colors are available upon request.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)
ASTM C33 - *Standard Specification for Concrete Aggregates*
ASTM C39 - *Concrete Compressive Strength*
ASTM C150 - *Standard Specification for Portland Cement*
ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*
ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*
ASTM C979 - *Pigments for Integrally Colored Concrete*

Physical / Chemical Properties

Classic Pilaster Cap weight is a minimum of 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.