



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Hexagonal Paver

### Manufacturer

Stepstone, Inc.  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-327-7474  
Fax 310-217-1424  
Toll free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete for over 40 years. Hexagonal Pavers are precast concrete pavers that come in many standard sizes. Hexagonal Pavers are designed to be used for both commercial and residential applications.

### Composition & Materials

Hexagonal Pavers are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

### Sizes

Hexagonal Pavers are available in standard sizes. 16" x 2" thickness, 20 1/2" and 24" x 2 1/2" thickness. Corner and Starter pieces also available. See Hexagonal Paver details for more size information.

### Finishes

Hexagonal Pavers available finishes include: light, medium or heavy sandblast

### Colors

Hexagonal Pavers are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

### Physical /Chemical Properties

Hexagonal Paver weight is 22-28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, Inc. for further information*

September 2019