



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474  
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

## MATERIAL PRODUCT DATA SHEET

### Product Name

Large Scale CalArc Paver

### Manufacturer

Stepstone, Inc.  
17025 So. Main St.  
Gardena, CA 90248

Phone 310-327-7474  
Fax 310-217-1424  
Toll free 800-572-9029

### Product Description

Stepstone has produced high quality precast concrete for over 40 years. Large Scale CalArc Pavers are precast concrete pavers that are designed for pedestrian use in both commercial and residential applications.

### Composition & Materials

Large Scale CalArc Pavers are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

### Sizes

Large Scale CalArc Pavers are available in standard sizes ranging from 11-7/8"x11-7/8" to 47-7/8" x 47-7/8" in 2- 1/2" thickness. See Large Scale CalArc Paver details for standard sizes.

### Finishes

Large Scale CalArc Paver available finishes include: Custom aggregates, light, medium, or heavy sandblast

### Colors

Large Scale CalArc Pavers are available in 12 standard colors: Almond, Cafe Brown, Kona, Caramel, French Gray, Granada White, Iceberg Green, Pebble, Santa Fe Buff, Brick Red, Agave, Porcelain; custom colors are available upon request.

### Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

### Physical /Chemical Properties

Large Scale CalArc Paver weight is 28 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

*Please contact Stepstone, Inc. for further information*

January 2018