



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Modern Pool Coping

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll Free 800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Modern Pool Coping provides distinctive good looks with high strength hardrock concrete. The Modern Pool Coping has a rolling 2" bullnose edge. They work well as a design element to refine any project. The system includes straights and corners. They are designed to be used for both commercial and residential applications.

Composition & Materials

Modern Pool Copings are hand-made, wet-cast from 4000 PSI hardrock concrete, using Type III cement.

Sizes

Modern Pool Coping straights are 18"x24"x2" and 18"x18"x2"; corners are 18"x18"x2".

Finishes

Modern Pool Coping available finishes include: fine grain stipple, and light, medium or heavy sandblast

Colors

Modern Pool Copings are available in 12 standard colors: Almond, Cafe Brown, Kona, Caramel, French Gray, Granada White, Iceberg Green, Pebble, Santa Fe Buff, Brick Red, Agave, Porcelain; custom colors are available upon request.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

Physical / Chemical Properties

Modern Pool Coping weight is 22 LBS per square foot. Water absorption: Not more than 6.0% average, not more than 7.0% for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, Inc. for further information

January 2018