



17025 SO. MAIN ST. GARDENA, CA 90248 | 310-327-7474
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | www.stepstoneinc.com

MATERIAL PRODUCT DATA SHEET

Product Name

Narrow Modular Paver by Stepstone®

Manufacturer

Stepstone, Inc.
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll free 1-800-572-9029

Product Description

Stepstone has produced high quality precast concrete for over 40 years. Narrow Modular Pavers by Stepstone® are precast concrete pavers that come in five standard sizes. Narrow Modular Pavers by Stepstone® are designed to be used for both commercial and residential applications.

Composition & Materials

Narrow Modular Pavers by Stepstone® are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

Sizes

Narrow Modular Pavers by Stepstone® are available in 2-7/8"x 8-7/8"x 4", 2-7/8"x 11-7/8"x 4", 2-7/8"x 17-7/8"x 4", 2-7/8"x 23-7/8"x 4", 5-7/8" x 11-7/8"x 4", 5-7/8" x 17-7/8"x 4, 5-7/8" x 23-7/8"x 4, 2-7/8"x 17-7/8"x 1" (vertical set tile veneer only), and 2-7/8"x 17-7/8"x 2-1/2" (tile: mortar set only).

Finishes

Narrow Modular Pavers by Stepstone® available finishes include: Custom aggregates, light, medium, or heavy sandblast

Colors

Narrow Modular Pavers by Stepstone® are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble, and Porcelain; custom colors are available upon request.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

Physical /Chemical Properties

Narrow Modular Pavers by Stepstone® weight varies by thickness: 4" thickness is 48 PSF; 2½" thickness is 28 PSF; 1" thickness is 12 PSF. Water absorption not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/-1/8" from standard dimensions. No unit will differ more than +/-1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, Inc. for further information

November 2018